

*Evolvecomp™ materials are biocompatible composite materials composed of bioresorbable matrix polymer reinforced with ultra-thin bioresorbable glass fibers. Evolvecomp™ materials are manufactured by using the ABMcomposite technology that ensures good adhesion between the matrix polymer and reinforcing fiber.*

## Evolvecomp™ GF40PLG85

**Description** Composite pellet composed of 85L/15G PLGA and bioresorbable glass fibers, IV 2.0

Specification	Property	Specification	Test method
	Appearance, colour	Opaque white, white	Visual
	Appearance, shape	Pellets	Visual
	Inherent viscosity of polymer	≥ 1.6 dl/g	Microviscometry
	Residual lactide monomer content	≤ 0.5 wt-%	Gas Chromatography (GC)
	Residual glycolide monomer content	≤ 0.5 wt-%	Gas Chromatography (GC)
	Glass content	40 ± 5 wt-%	Ignition loss
	Total heavy metal content	≤ 10 ppm (minus Sn)	ICP-MS
	Tin content	≤ 100 ppm	ICP-MS

Certificate of analysis is provided for each batch, showing the analytical results.

**Packaging** Pellets are packaged in to a double polymer pouch. Outer pouch contains aluminum barrier layer. Maximum amount in a package is 1 kg.

**Storage and Handling** Pellets to be stored below or at -15 °C temperature.

DISCLAIMER: Determining the suitability of these materials for any applications, complying with legal requirements for any such applications, are the sole responsibility and obligation of anyone purchasing these materials for such applications. The information in this Data Sheet is given according to our best knowledge at the date shown in header. This data sheet is for informative purpose only and all specifications need to be discussed and agreed with Arctic Biomaterials Oy separately.

ARCTIC BIOMATERIALS OY MAKES NO WARRANTY, EXPRESS OR IMPLIED, REGARDING THE INFORMATION CONTAINED HEREIN OR ITS PRODUCTS, INCLUDING BUT NOT LIMITED TO ANY WARRANTY AS TO ACCURACY OR COMPLETENESS OF INFORMATION, OR ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.